



STEATITE SPECIFICATIONS

	Property	ASTM Method	Units	Steatite L-4	Steatite L-5
General	Crystal Size (Average)	Thin Section	Microns	7	7
	Color	--	--	Tan	Gray-Green
	Water Absorption	C 20-97	%	0	0
Mechanical	Density	C 20-97	g/cc	2.65	2.75
	Hardness	Vickers 500 gm	GPa (kg/mm ²)	4.9 (500)	4.9 (500)
	Hardness	--	R45N	57	57
	Flexural Strength (MOR) (3 point) @ RT	F417-87	MPa (psi x 10 ³)	117 (17)	138 (20)
	Tensile Strength @ RT	--	MPa (psi x 10 ³)	103 (15)	103 (15)
	Compressive Strength @ RT	--	MPa (psi x 10 ³)	551 (80)	586 (85)
	Elastic Modulus	C848	GPa (psi x 10 ⁶)	103 (15)	103 (15)
	Poisson's Ratio	C848	--	0.24	0.24
Thermal	C.T.E. 25 - 100° C	C 372-96	x 10 ⁻⁶ /C	7.3	8.5
	C.T.E. 25 - 300° C	C 372-96	x 10 ⁻⁶ /C	7.4	8.6
	C.T.E. 25 - 600° C	C 372-96	x 10 ⁻⁶ /C	7.5	8.6
	Thermal Conductivity @ RT	C 408	W/m K	3	3
	Max Use Temp	--	Fahrenheit (°F)	2350	2350
		--	Celsius (°C)	1290	1290
Electrical	Dielectric Strength (.125" Thick)	D 149-97A	V/mil	260	270
	Dielectric Constant @ 1 MHz	D 150-98	--	5.6	5.7
	Dielectric Constant	D 2520-95	--	5.6	5.8
	@ Gigahertz			9.2	12.5
	Dielectric Loss @ 1 MHz	D 150-98	--	0.003	0.0014
	Dielectric Loss	D 2520-95	--	0.005	0.0017
	@ Gigahertz			9.2	12.5
	Volume Resistivity, 25°C	D 257	ohms-cm	> 1 x 10 ¹⁴	> 1 x 10 ¹⁴
	Volume Resistivity, 300° C	D 1829	ohms-cm	2 x 10 ¹⁰	1 x 10 ¹¹
	Volume Resistivity, 500° C	D 1829	ohms-cm	1 x 10 ⁹	4 x 10 ¹⁰
Volume Resistivity, 700° C	D 1829	ohms-cm	2 x 10 ⁸	1 x 10 ⁹	

CONTACT US

Superior Technical Ceramics | 600 Industrial Park Rd. | St. Albans, VT 05478 | www.ceramics.net

Telephone: (802) 527-7726 | Fax: (802) 527-1181 | Email: sales@ceramics.net

Superior Technical Ceramics products and services are subject to the Company's standard terms and conditions, available on request or at ceramics.net. For more information contact an authorized Superior Technical Ceramics representative. Unless noted otherwise, trademarks and service marks herein are the property of Superior Technical Ceramics and may be registered in the United States and/or other countries. Superior Technical Ceramics products named herein may be protected by one or more U.S. and/or foreign patents. For more information, contact sales@ceramics.net. Specifications are subject to change without notice. Superior Technical Ceramics sells its products and services in accordance with the terms and conditions set forth in the applicable contract between Superior Technical Ceramics and the client.

