

SECTION 1: Identification

Product identifier

Product name Dense Alumina Ceramic

Substance name Aluminum Oxide

 Al_2O_3

Other names / synonyms Alumina Ceramic; AL 74, AL 85, Al 94, AL 95, AL 96, AL 96P, AL 98, AL

98P, AL 995, AL 998, AL 9980, AL999

Recommended use of the chemical and restrictions on use

Technical Ceramic Components

Supplier's details

Name Superior Technical Ceramics
Address 600 Industrial Park Road
St. Albana, Vermont 05 170

St. Albans, Vermont 05478

USA

Telephone 802-527-7726 Fax 802-527-1181

Emergency phone number(s)

802-527-7726

SECTION 2: Hazard identification

This product is considered an article and does not pose any health hazard under normal use. The health effects listed below may be relevant when dust is generated during machining or other processing conditions.

Classification of the substance or mixture

Not a hazardous substance or mixture.

GHS label elements, including precautionary statements

Not a hazardous substance or mixture.

Other hazards which do not result in classification

Not a hazardous substance or mixture.

SECTION 3: Composition/information on ingredients

Components

1. Aluminum oxide

Concentration > 70 - 100 % (Weight)

CAS no. 1344-28-1

2. Glassy Phase

Concentration 0 - 30 % (Weight)

Other names / synonyms

Glassy Phase 60676-86-0

CAS no.

SECTION 4: First-aid measures

Description of necessary first-aid measures

General advice Hazard is principally that of a nuisance dust only as a byproduct of

machining. Coughing or shortness of breath may occur in cases of

excessive inhalation.

If inhaled Move to fresh air and consult with local medical personnel if discomfort

persists.

In case of skin contact Wash affected area with soap and water and consult with local medical

personnel if irritation persists.

In case of eye contact Flush with tepid water for a minimum of 15 minutes and consult with local

medical personnel if discomfort persists.

If swallowed Administer water to dilute, but not if person is unconscious. Consult with

local medical personnel if discomfort persists.

SECTION 5: Fire-fighting measures

Suitable extinguishing media

Use any means suitable for extinguishing surrounding fire.

Special protective actions for fire-fighters

Use protective clothing and breathing equipment appropriate for the surrounding fire.

SECTION 6: Accidental release measures

Methods and materials for containment and cleaning up

Any dust from machining should be wet mopped or dry vacuumed.

SECTION 7: Handling and storage

Precautions for safe handling

Any dust from machining should be wet mopped or dry vacuumed.

SECTION 8: Exposure controls/personal protection

Control parameters

1. alpha-Alumina (CAS: 1344-28-1)

PEL (Inhalation): see PNOR (Cal/OSHA)
OSHA Annotated Table Z-1, www.osha.gov

2. alpha-Alumina (CAS: 1344-28-1)

REL (Inhalation): See Appendix D (NIOSH) OSHA Annotated Table Z-1, www.osha.gov

3. alpha-Alumina, Total dust (CAS: 1344-28-1)

PEL (Inhalation): 15 mg/m3 (OSHA)
OSHA Annotated Table Z-1, www.osha.gov

4. alpha-Alumina, Total dust (CAS: 1344-28-1)

PEL (Inhalation): 10 mg/m3 (Cal/OSHA) OSHA Annotated Table Z-1, www.osha.gov

5. alpha-Alumina, Respirable fraction (CAS: 1344-28-1)

PEL (Inhalation): 5 mg/m3 (OSHA)

OSHA Annotated Table Z-1, www.osha.gov

6. alpha-Alumina, Respirable fraction (CAS: 1344-28-1)

PEL (Inhalation): 5 mg/m3 (Cal/OSHA) OSHA Annotated Table Z-1, www.osha.gov

Appropriate engineering controls

Local or general exhaust ventilation recommended while machining.

Individual protection measures, such as personal protective equipment (PPE)

Eye/face protection

Safety goggles in the presence of airborne dust.

Skin protection

Polymer gloves for prolonged dust exposure.

Respiratory protection

NIOSH/MSHA approved respirator for dust when exposure limit is exceeded.

SECTION 9: Physical and chemical properties

Information on basic physical and chemical properties

Appearance/form White, Cream or Purple Solid

Odor Odorless
Odor threshold
pH

Odorless
N/A
N/A

Melting point >1643°C (2990°F)

Initial boiling point and boiling range N/A Flash point N/A Evaporation rate N/A Flammability (solid, gas) N/A Upper/lower flammability limits N/A Upper/lower explosive limits N/A Vapor pressure N/A Vapor density N/A Relative density >3.0g/cc

Solubility(ies) Insoluble in water

Partition coefficient: n-octanol/water N/A
Auto-ignition temperature N/A

Decomposition temperature N/A
Viscosity N/A
Explosive properties N/A
Oxidizing properties N/A

SECTION 10: Stability and reactivity

Chemical stability

Stable

Conditions to avoid

Certain extreme acidic conditions (consult manufacturer for cautionary advice).

SECTION 11: Toxicological information

No Applicable Information Found

SECTION 12: Ecological information

No Applicable Information Found

SECTION 13: Disposal considerations

Disposal of the product

This material is not hazardous per 40 CFR 261. Consultation with federal, state and local officials is recommended before disposal.

SECTION 14: Transport information

DOT (US)

Not dangerous goods

IMDG

Not dangerous goods

IATA

Not dangerous goods

SECTION 15: Regulatory information

US FEDERAL

TSCA

CAS# 1344-28-1 is listed on the TSCA inventory. CAS# 60676-86-0 is listed on the TSCA inventory.

SARA Section 302 Extremely Hazardous Substances

None of the chemicals in this product have a TPQ.

Section 313

CAS# 1344-28-1 is reported under Section 313.

OSHA:

None of the chemicals in this product are considered highly hazardous by OSHA.

US STATE

CAS# 1344-28-1 can be found on the following state right to know lists:

Illinois, Minnesota, Massachusetts, New Jersey, Pennsylvania, Texas. Consult your state and local resources for further information.

California Prop 65

Substance Not Listed

SECTION 16: Other information

Further information/disclaimer

Although reasonable care has been taken to provide accurate and current information in preparation of this document, Superior Technical Ceramics extends no warranties, makes no representation and assumes no responsibility for any loss, damage, or injury of any kind which may result from reliance of information provided in this document by any person.

Preparation Information

Prepared by: Superior Technical Ceramics 1-802-527-7726 lab@ceramics.net

Prepared on: June 1, 2015

Last Revision: -- verified March 22, 2024