

## SILICON NITRIDE $(Si_3N_4)$ SPECIFICATIONS

From prototyping to materials design consulting to custom manufacturing, our engineers will work with you to develop unique solutions for your most extreme environmental and technical challenges. We're large enough to have complete inhouse capabilities while remaining small enough to provide attentive and timely service.

	Property	ASTM Method	Units	Silicon Nitride (Si <sub>3</sub> N <sub>4</sub> )
General	Crystal Size (Average)	Thin Section	Microns	4
	Color			Black
	Gas Permeability		atms-cc/sec	gas tight <10 <sup>-10</sup>
	Water Absorption	C 20-97	%	0
Mechanical	Density	C 20-97	g/cc	3.25
	Hardness	Vickers 500 gm	GPa (kg/mm²)	15 (1529)
	Hardness		R45N	83
	Fracture Toughness	Notched Beam	MPam <sup>1/2</sup>	6
	Flexural Strength (MOR) (3 point) @ RT	F417-87	MPa (psi x 10 <sup>3</sup> )	900 (130)
	Tensile Strength @ RT		MPa (psi x 10 <sup>3</sup> )	537 (78)
	Compressive Strength @ RT		MPa (psi x 10 <sup>3</sup> )	2500 (362)
	Elastic Modulus	C848	GPa (psi x 10°)	300 (44)
	Poisson's Ratio	C848		0.28
Thermal	C.T.E. 25 - 600° C	C 372-96	x 10 <sup>-6</sup> /C	2.9
	Thermal Conductivity @ RT	C 408	W/m K	29
	Max Use Temp		Fahrenheit (°F)	2552
			Celsius (°C)	1400
Electrical	Dielectric Strength (.125" Thick)	D 149-97A	V/mil	300
	Dielectric Constant @ 1 MHz	D 150-98		9.2
	Volume Resistivity, 25°C	D 257	ohms-cm	> 1 x 10 <sup>14</sup>

## CONTACT US

Superior Technical Ceramics | 600 Industrial Park Rd. | St. Albans, VT 05478 | <u>www.ceramics.net</u> Telephone: (802) 527-7726 | Fax: (802) 527-1181 | Email: sales@ceramics.net

Superior Technical Ceramics products and services are subject to the Company's standard terms and conditions, available on request or at ceramics.net. For more information contact an authorized Superior Technical Ceramics representative. Unless noted otherwise, trademarks and service marks herein are the property of Superior Technical Ceramics and may be registered in the United States and/or other countries. Superior Technical Ceramics products named herein may be protected by one or more U.S. and/or foreign patents. For more information, contact sales@ceramics.net. Specifications are subject to change without notice. Superior Technical Ceramics sells its products and services in accordance with the terms and conditions set forth in the applicable contract between Superior Technical Ceramics and the client.

A53130 8

INA